







TURNOUT FABRICS

DuPont™
Nomex.
NEVER QUIT.™

DuPont™
Kevlar.

OUTER SHELL



PBI MAX™ GOLD

Proprietary blend of 70% “PBI Dominant” PBI / Kevlar® spun yarns with 30% Kevlar® filament Twill weave.

Nominal weight of 7.0 or 6.0 oz/yd²

PBI MAX™ BLACK

Proprietary blend of 70% “PBI Dominant” PBI / Kevlar® spun yarns with 30% Kevlar® filament Twill weave.

Nominal weight of 7.0 or 6.0 oz/yd²

PBI MAX LP™ GOLD



Proprietary blend of 70% “PBI LP” / para-aramid spun yarns with 30% 400-denier DuPont Kevlar® filament, Comfort Twill with Filament Twill Technology

Nominal weight of 6.0 oz/yd²

PBI MAX LP™ BLACK

Proprietary blend of 70% “PBI LP” / para-aramid spun yarns with 30% 400-denier DuPont Kevlar® filament, Comfort Twill with Filament Twill Technology

Nominal weight of 6.0 oz/yd²



PBI PEAK 5™ GOLD

Proprietary blend of 40% PBI / 60% 400-denier DuPont Kevlar®, Comfort Twill with Filament Twill Technology, Durasoft Pro™ Finish

Nominal weight of 5.6 oz/yd²

PBI PEAK 5™ BLACK

Proprietary blend of 40% PBI / 60% 400-denier DuPont Kevlar®, Comfort Twill with Filament Twill Technology, Durasoft Pro™ Finish

Nominal weight of 5.6 oz/yd²

PBI® XT GOLD

Proprietary blend of 40% PBI / 60% 400-denier DuPont Kevlar®.

Nominal weight of 7.5 oz/yd²

PBI® XT BLACK

Proprietary blend of 40% PBI / 60% 400-denier DuPont Kevlar®.


Nominal weight of 7.5 oz/yd²



ARMOR AP™
GOLD

Proprietary blend of 80% Nomex® / Kevlar® spun yarns with 20% 400-denier Kevlar® filament Twill weave, Teflon® F-PPE water repellent finish.

Nominal weight of 6.5 oz/yd²



ARMOR AP™
KHAKI

Proprietary blend of 80% Nomex® / Kevlar® spun yarns with 20% 400-denier Kevlar® filament Twill weave, Teflon® F-PPE water repellent finish.

Nominal weight of 6.5 oz/yd²



ARMOR AP™
BLACK

Proprietary blend of 80% Nomex® / Kevlar® spun yarns with 20% 400-denier Kevlar® filament Twill weave, Teflon® F-PPE water repellent finish.

Nominal weight of 6.5 oz/yd²



BRIGADE® 750
YELLOW

93% Nomex® / 5% Kevlar® / 2% Carbon

Plain weave; durable water repellent finish

Nominal weight of 7.5 oz/yd²



BRIGADE® 750
TAN

93% Nomex® / 5% Kevlar® / 2% Carbon

Plain weave; durable water repellent finish

Nominal weight of 7.5 oz/yd²




BRIGADE® 750
NATURAL

93% Nomex® / 5% Kevlar® / 2% Carbon

Plain weave; durable water repellent finish

Nominal weight of 7.5 oz/yd²




BRIGADE® 750
BLACK

93% Nomex® / 5% Kevlar® / 2% Carbon

Plain weave; durable water repellent finish

Nominal weight of 7.5 oz/yd²




PIONEER™
YELLOW

100% aramid blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²




PIONEER™
LIGHT GOLD

100% aramid blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²



PIONEER™
GOLD

100% aramid blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²




PIONEER™
KHAKI

100% aramid blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²



PIONEER™
BLACK

100% aramid blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²



AGILITY™
LIGHT GOLD

Aramid / PBO blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²




AGILITY™
DARK GOLD

Aramid / PBO blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²



AGILITY™
BLACK GOLD

Aramid / PBO blend

Twill weave; Super Shelltite™

Nominal weight of 6.6 oz/yd²




Flex7™
Natural Gold

Para-Aramid / PBI blend

Twill weave

Nominal weight of 6.9 oz/yd²



Flex7™

Black

Para-Aramid / PBI blend

Twill weave

Nominal weight of 6.9
oz/yd²

THERMAL BARRIERS



Q-8™

3.4 oz/yd² 50% meta-aramid/50% FR modacrylic face cloth, quilted to a 4.6 oz/yd² 80% reprocessed aramid/20% FR Rayon



Caldura® SL2i

3.8 oz/yd² 61% para-aramid/34% FR rayon/5% nylon face cloth, quilted to 1 layer of 2.3 oz/yd² and 1 layer of 1.5 oz/yd² meta-aramid/para-aramid non-woven batting

Nominal weight of 7.7 oz/yd²



Caldura® with Nomex® Nano

61% aramid / 34% Rayon / 5% Nylon face cloth quilted to Nomex® ELITE Nano and 1 layer of 100% aramid substrate

Nominal weight of 6.7 oz/yd²



Quantum 3D® SL2i

3.8 oz/yd² 61% para-aramid/34% FR rayon/5% nylon face cloth, quilted to 1 layer of 2.3 oz/yd² and 1 layer of 1.5 oz/yd² meta-aramid/para-aramid non-woven batting

Nominal weight of 7.7 oz/yd²



Glide Ice™ Pure

3.8 oz/yd² 86% aramid/14% FR viscose twill weave face cloth, quilted to 1 layer of a 4.0 oz/yd² 50% meta-aramid/50% para-aramid needlepunch batting

Nominal weight of 7.6 oz/yd²



Glide Ice™ 1-layer

3.6 oz/yd² 86% Aramid/14% Viscose Twill Weave Quilted to 1 layer of 2.3oz/yd² Aramid

Nominal weight: 5.9 oz/yd²



Glide Ice™ 2-layer

3.6 oz/yd² 86% aramid/14% FR viscose twill weave face cloth, quilted to 1 layer of a 2.3 oz/yd² and 1 layer of 1.5 oz/yd² E89™ spunlace


Nominal weight of 7.4 oz/yd²



Glide Ice™ w/ G2

3.6 oz/yd² 86% aramid/14% FR viscose twill weave face cloth, quilted to 1 layer of 1.8 oz/yd² and 1 Layer of 1.4 oz./yd² 80% meta-aramid/20% PBI non-woven batting

Nominal weight of 6.8 oz/yd²



Glide Ice™ with Nomex® Nano

3.6 oz/yd² Glide Ice™ face cloth consisting of 60% DuPont™ Nomex® filament and 40% DuPont™ Nomex®/Lenzing FR spun yarns quilted to 1 layer of 0.6 oz./yd² Nomex® Nano and 1 layer of 2.3 oz./yd² DuPont™ Nomex® E89™ spunlace

Nominal weight of 6.5 oz/yd²



Defender® M NP

Brass

3.2 oz/yd² FR rayon/aramid/nylon plain weave face cloth, quilted to 1 layer of 3.8 oz/yd² aramid needlepunch batting

Nominal weight of 7.0 oz/yd²



Defender® M SL2

Brass

3.2 oz/yd² FR rayon/aramid/nylon plain weave face cloth, quilted to 2 layer of 2.3 oz/yd² of meta-aramid/para-aramid non-woven batting

Nominal weight of 7.8 oz/yd²




Defender® M SL2

Universal Camo

3.2 oz/yd² FR rayon/aramid/nylon plain weave face cloth, quilted to 2 layer of 2.3 oz/yd² of meta-aramid/para-aramid non-woven batting

Nominal weight of 7.8 oz/yd²



Prism™ Pure

3.6 oz/yd² 68% aramid / 21% FR viscose / 11% polyamide Dobby weave face cloth, quilted to 1 layer of 4.0 oz/yd² of 50% meta-aramid and 50% para-aramid needlepunch batting

Nominal weight of 7.6 oz/yd²



Prism™ 2-layer

3.6 oz/yd² 68% aramid / 21% FR viscose / 11% polyamide Dobby weave face cloth, quilted to 1 layer of a 2.3 oz/yd² and 1 layer of 1.5 oz/yd² E89™ spunlace


Nominal weight of 7.4 oz/yd²



Titanium® with Nomex® Nano

3.8 oz/yd² aramid / FR rayon / Nylon face cloth, quilted to 1 layer of a 2,3 oz/yd² aramid spunlace batting

Nominal weight of 6.7 oz/yd²




Titanium® SL2i

3.8 oz/yd² aramid / FR rayon / Nylon face cloth, quilted to 1 layer of a 2,3 oz/yd² and 1 layer of 1.5 oz/yd² meta-aramid/para-aramid non-woven batting

Nominal weight of 7.7 oz/yd²

MOISTURE BARRIERS



GORE® RT7100 moisture barrier – Type 3D

GORE® RT7100 moisture barrier – Type 3D, comprised of a GORE® membrane and a 3.0 oz/yd² needle-punched non-woven Nomex® substrate.

Nominal weight of 4.6 oz/yd²



CROSSTECH® Black moisture barrier – Type 2F

Two-layer CROSSTECH® black moisture barrier – Type 2F, comprised of a CROSSTECH™ membrane laminated to a 3.3 oz/yd² Nomex® IIIA woven pajama-check substrate.

Nominal weight of 4.7 oz/yd²



CROSSTECH® 3-Layer moisture barrier – Type 4A

CROSSTECH® 3-Layer moisture barrier – Type 4A, comprised of a CROSSTECH® membrane laminated to a 3.3 oz/yd² Nomex® IIIA woven pajama-check substrate and a 1.8 oz/yd² Nomex® woven fabric.

Nominal weight of 7.0 oz/yd²



GORE® PARALLON™

The GORE® PARALLON™ liner system consists of three separable layers. The outermost layer is comprised of a 3.3 ounce per square yard Nomex® IIIA woven pajama check substrate laminated to a proprietary GORE ePTFE film. The middle layer is comprised of a 4.1 ounce per square yard Meta-aramid/Para-aramid three dimensional non-woven batting laminated to a proprietary GORE ePTFE film. The innermost layer which functions as the moisture barrier, is comprised of a 3.6 ounce per square yard 86% aramid/ 14% FR rayon twill weave facecloth laminated to an enhanced bicomponent membrane from W.L. Gore and Associates, Inc.



STEDAIR® 3000

STEDAIR® 3000 combines a spunlace substrate with a bi-component membrane using a combination of microporous and monolithic film technologies.

Nominal weight of 5.2 oz/yd²



STEDAIR® 4000

STEDAIR® 4000 combines a woven Nomex® IIIA pajama check substrate with a bi-component membrane using a combination of microporous and monolithic film technologies.

Nominal weight of 5.5 oz/yd²



STEDAIR® Gold

STEDAIR® Gold combines a woven Kevlar® / Nomex® / PBI substrate with a bi-component membrane using a combination of microporous and monolithic film technologies.

Nominal weight of 5.2 oz/yd²



STEDAIR® Clear

This moisture barrier features an all-new non-fluorinated membrane technology certified to NFPA 1971. STEDAIR® CLEAR is constructed of a 3.2 oz woven meta-aramid pajama check laminated to a non-fluorinated barrier with a highly engineered polymer coating.

Nominal weight of 4.24 oz/yd²

REINFORCEMENT



Polymer coated aramid
GRAY




Polymer coated aramid
GOLD



Polymer coated aramid
BLACK

PARTNERS



Classified by UL to NFPA 1971:2018

INNOTEX®

2397 Harts Ferry Rd., Ohatchee, Alabama
USA 36271

INNOTEX®

275 Gouin, Richmond, Quebec
Canada JOB 2H0

Customer Service

1 888 821 3121 (U.S. and Canada only)
Tel.: 819 826-5971
Fax: 819 826-5195

Email: info@innotexprotection.com
www.innotexprotection.com

® Registered Trademark of INNOTEX INC. or their respective holders.

™ Trademark of INNOTEX INC. or their respective holders.

Printed in Canada / REV. 04-16

Copyright 2024 INNOTEX INC.

All rights reserved. Because of our ongoing commitment to product quality and development we reserve the right to change, cancel, discontinue or alter any specification, design or feature without prior notice and without incurring obligation.

Disclaimer : The portrayed situations are fictional and no attempt should be made to reproduce them.